



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 013 291 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
28.06.2000 Bulletin 2000/26

(51) Int. Cl.⁷: **A61L 15/58**, A61L 15/60

(21) Application number: **99125404.6**

(22) Date of filing: **20.12.1999**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **21.12.1998 US 217318**

(71) Applicant: **McNEIL-PPC, INC.**
Skillman, New Jersey 08558 (US)

(72) Inventor: **Luizzi, Joseph**
Newton, PA 18940 (US)

(74) Representative:
Groening, Hans Wilhelm, Dipl.-Ing.
BOEHMERT & BOEHMERT
Franz-Joseph-Strasse 38
80801 München (DE)

(54) **Hot melt adhesive comprising an absorbent**

(57) A hot-melt adhesive containing fluid absorbing polymers and non-absorbing polymers is optionally blended with super-absorbent polymers. The resulting thermoplastic hot-melt adhesive material can be used to adhesively bond substrates such as polymeric films together, as well as, to provide additional liquid absorption capacity to non-woven fabrics or absorbent structures. This adhesively coated material is particularly useful in the construction of absorbent products such as catamenial devices, wound dressings, bandages, and diapers and the like.

EP 1 013 291 A1

Description

FIELD OF THE INVENTION

5 [0001] The present invention relates to a novel adhesive and more particularly to a hot-melt adhesive which is capable of absorbing liquids.

BACKGROUND OF THE INVENTION

10 [0002] Absorbent articles such as catamenial pads, diapers, bandages, nursing pads and the like generally contain an absorbent element. The absorbent element of conventional disposable articles is typically formed from a fiberized wood pulp fluff or absorbent non-woven and/or other synthetic or natural absorbent materials such as peat moss or super-absorbent polymers. The absorbent element is covered with a soft, flexible liquid permeable topsheet which allows body fluid to be absorbed into the fluid retaining absorbent element. Typically a fluid impermeable backsheet is
15 adhesively affixed to the liquid permeable topsheet around a peripheral edge margin to form a flange seal and thereby fully enclose the absorbent element to prevent fluid leakage.

[0003] Hot melt adhesives are typically used in the construction of absorbent articles to attach the liquid permeable topsheet to the absorbent element and also to attach the fluid impermeable backsheet to the element. In addition, hot melt adhesives are also used in the construction of the absorbent structures to laminate multiple plies together or to
20 adhesively affix absorbent particles to a non-woven fabric or fibrous pulp.

SUMMARY OF THE INVENTION

[0004] It is an object of the present invention to provide a hot-melt adhesive which is capable of absorbing aqueous
25 liquids.

[0005] It is another object of the present invention to provide a hot melt adhesive that eliminates the risk of super absorbent particles causing pinholes in a barrier backsheet when the absorbent article has been subjected to embossing or channeling.

[0006] It is another object of the present invention to provide a hot melt adhesive that eliminates the need to handle
30 powders during the application of super absorbent particles to absorbent products.

[0007] It is another object of the present invention to provide a hot melt adhesive which enables superabsorbent particles to be pattern coated onto a substrate.

[0008] It is another object of the present invention to provide a hot melt adhesive which also functions as a fluid retaining system.

35 [0009] In accordance with the present invention, there has been provided a novel hot-melt adhesive that is capable of absorbing aqueous liquids which comprises:

about 10% to about 50% of a block copolymer;
about 20% to about 80% of a tackifying resin; and
40 about 1% to about 60% of an aqueous liquid-absorbing polymer.

[0010] Also provided in accordance with the present invention is an absorbent article, the absorbent article comprising a liquid permeable topsheet, a liquid impermeable barrier sheet, an absorbent element between the topsheet and the barrier sheet, wherein either the topsheet or the barrier sheet is adhered to the absorbent element with a hot
45 melt adhesive which further comprises:

about 10% to about 50% of a block copolymer;
about 20% to about 80% of a tackifying resin; and
50 about 1% to about 60% of an aqueous liquid-absorbing polymer.

[0011] Also provided in accordance with the present invention is an absorbent article, the absorbent article comprising a liquid permeable topsheet, a liquid impermeable barrier sheet, an absorbent element between the topsheet and the barrier sheet, wherein at least a portion of the absorbent element contains a hot melt adhesive which further
55 comprises:

about 10% to about 50% of a block copolymer;
about 20% to about 80% of a tackifying resin; and
about 1% to about 60% of an aqueous liquid-absorbing polymer.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012]

- 5 Fig. 1 is a top plan view of a sanitary napkin having a pattern coating.
- Figs. 2 is a side view of the sanitary napkin in Figure 1 taken through line A-A showing the adhesive applied between a cover layer and an absorbent element.
- 10 Fig. 3 is a top plan view of a sanitary napkin having a zone coating.
- Fig. 4 is a top plan view of a sanitary napkin having a foamed adhesive in a pattern which forms side and end gas-kets.
- 15 Fig. 5 is a side view of the sanitary napkin of Figure 4 taken through line B-B showing the adhesive applied on an upper surface of a cover layer of the napkin.
- Fig. 6 is a top plan view of a sanitary napkin having a multi-line adhesive pattern.
- 20 Fig. 7 is a side view of the sanitary napkin of figure 6 taken through line C-C showing the adhesive applied between a barrier layer and an absorbent element.
- Fig. 8 is a top plan view of a sanitary napkin having adhesive applied in a curved line pattern adjacent each longitudinal side edge and transverse end region of the napkin.
- 25 Fig. 9 is a top plan view of a sanitary napkin having adhesive applied in a curved line pattern which forms a closed perimeter around a center region of the sanitary napkin.
- Fig. 10 is a top plan view of a sanitary napkin having adhesive applied in an hour glass pattern in a central region of the napkin.
- 30 Fig. 11 is a top plan view of a sanitary napkin having adhesive applied as a pair of substantially parallel lines adjacent each longitudinal side edge of the napkin.
- 35 Fig. 12 is a side view of the sanitary napkin of Figure 11 taken through lines D-D of Figure 11 showing the adhesive applied between a cover layer and an absorbent element of the napkin.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

- 40 [0013] The present invention relates to hot melt adhesives, and more particularly to hot melt adhesives which are useful in the construction of absorbent articles such as catamenial pads, diapers, breast pads, surgical pads and bandages. Unlike traditional hot melt adhesives that are hydrophobic in nature, the hot-melt adhesives of the present invention readily absorb aqueous fluids such as saline and menstrual fluid. The hot melt adhesives of the present invention are formed from a blend of about 10% to about 50% of a block copolymer; about 20% to about 80% of a tackifying resin;
- 45 and about 1% to about 60% of an aqueous liquid-absorbing polymer. The hot melt adhesives of the present invention may optionally contain absorbent thermoplastic polymers, super absorbent particles, tackifiers and plasticizers.
- [0014] In a preferred embodiment, the hot melt adhesives of the present invention comprise (by weight):

- 50 about 10 - 50% block copolymer;
 about 20 - 80% tackifying resin;
 about 1 - 60% aqueous liquid absorbing polymer;
 about 0 - 40% plasticizer; and
 about 0 - 2.0% antioxidant.

- 55 [0015] Suitable block copolymers for use in the invention include linear or radial co-polymer structures having the formula $(A-B)_x$ wherein block A is a polyvinylarene block, block B is a poly(monoalkenyl) block, x denotes the number of polymeric arms, and wherein x is an integer greater than or equal to one. Suitable block A polyvinylarenes include, but are not limited to Polystyrene, Polyalpha-methylstyrene, Polyvinyltoluene, and combinations thereof. Suitable Block

B poly(monoalkenyl) blocks include, but are not limited to conjugated diene elastomers such as for example polybutadiene or polyisoprene or hydrogenated elastomers such as ethylene butylene or ethylene propylene or polyisobutylene, or combinations thereof. Commercial examples of these types of block copolymers include Kraton™ elastomers from Shell Chemical Company, Vector™ elastomers from Dexcel, Solprene™ from Enichem Elastomers and Stereon™ from Firestone Tire & Rubber Co.

[0016] Suitable tackifying resins include natural and modified resins; glycerol and pentaerythritol esters of natural and modified resins; polyterpene resins; copolymers and terpolymers of natural terpenes; phenolic modified terpene resins and the hydrogenated derivatives thereof; aliphatic petroleum resins and the hydrogenated derivatives thereof; aromatic petroleum resin and the hydrogenated derivatives thereof; and aliphatic or aromatic petroleum resins and the hydrogenated derivatives thereof, and combinations thereof. Commercial examples of these types of resins include Foral® hydrogenated rosin ester, Staybelite® hydrogenated modified rosin, Poly-pale® polymerized rosin, Permalyne® rosin ester, Pentalyne® rosin ester, Adtac® oil extended hydrocarbon resin, Piccopale® aromatic hydrocarbon, Piccotac®, Hercotac® aromatic modified aliphatic hydrocarbon, Regalrez® cycloaliphatic resins, or Piccolyte® from Hercules, Eselementz® from Exxon Chemical aliphatic hydrocarbon and cycloaliphatic resins, Wingtack® from Goodyear Tire & Rubber Co. synthetic polyterpene resins including aromatic modified versions, Arkon® partially and fully hydrogenated aromatic resins from Arakawa Chemicals, Zonatac® styrenated terpene resin, Zonarez® rosin ester and Zonester® rosin ester from Arizona Chemical and Nevtac® aromatic modified aliphatic hydrocarbon from Neville Chemical Company.

[0017] Suitable aqueous liquid absorbing polymers include thermoplastic hydrogels such as superabsorbent materials or thermoplastic polymeric compositions, which are formed from a water-soluble soft segment and one or more hard segments. The hard segment must melt processable, i.e. at use temperature the hard segments in the polymer are below their melt temperature, and at process temperature, the hard segments are above their melting point temperature and below the decomposition temperature of either the other components of the hot-melt adhesive composition. The hard segment is substantially insoluble in water, and phase separates from the soft segment. Examples of suitable hard segments include, but are not limited to polyurethane, polyamides, polyesters, polyureas, and combinations thereof. Examples of suitable soft segments include, but are not limited to polyethylene oxide, polyvinyl alcohol, polyvinyl pyrrolidone, polyacrylamide, polysaccharide, polymaleic anhydride, random copolymers of polyethylene oxide and polypropylene-oxide and combinations thereof. The soft and hard segments may be covalently bonded together by means of urethane, amide, ester, or secondary urea linkages or combinations thereof. Examples of aqueous liquid absorbing thermoplastic polymeric compositions which are commercially available include hydrophilic polyurethane from Tyndale Plains-Hunter Ltd. and Aquacaulk® thermoplastic polymers from Sumitomo Seika Chemicals Co., Ltd.

[0018] Suitable superabsorbent materials include any of the conventional superabsorbent particles or superabsorbent fibers which are commercially available today. The superabsorbent material is preferably a superabsorbent particle having an average particle size less than 150 microns. An example of which is Aquakeep® J-550P from Absorbent Technologies Inc.

[0019] Suitable plasticizers for use in the present invention generally will include any conventional plasticizers which decrease hardness and modulus, enhance pressure sensitive tack and reduce melt and solution viscosity. It is preferred that the plasticizer be water soluble or water dispersible or alternatively be a wax-like substance such as polyethylene glycol, glycerin, glycerol, polypropylene glycol, butylene glycol or sorbitol. An example of a preferred plasticizer is Carbowax® polyethylene glycol from Union Carbide.

[0020] Suitable anti-oxidants for use in the present invention include any conventional anti-oxidants, and are preferably hindered phenols such as for example Ethanox 330™ 1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl) benzene which is commercially available from the Ethyl Corporation.

[0021] The hot melt adhesives of the present invention may be formed by blending the block copolymer, the tackifying resin and the aqueous liquid-absorbing polymer in a suitable adhesive processing equipment such as a melt mixer or extruder at a temperature above their respective melting points until uniformly mixed. The hot melt adhesive may be applied to substrates using conventional adhesive application equipment such as a hot melt adhesive slot coating head, a hot melt adhesive swirl spray applicator (a commercial example of which is a Nordson Control Fiberization®), using a hot melt adhesive micro fiber applicator (commercial examples of these applicators include Nordson Control Coat®, ITW Dynafiber®, J&M Meltblown, and May Coating's Accufiber®), using a hot melt adhesive rotary screen applicator to create a pattern coating (examples of this equipment include Nordson and Kraemer rotary screen technology).

[0022] Referring to Figure 1, there is shown an absorbent article, which for purposes of illustration is a sanitary napkin 1 having opposite longitudinal sides 2, 3 and opposite transverse ends 4, 5. Referring to Figure 2, the sanitary napkin 1 of Figure 1 is shown in cross section, having an upper, body facing, cover layer 10, a lower garment facing, barrier layer 20 and absorbent element 30 between the cover layer 10 and barrier layer 20. Liquid absorbing hot melt adhesive 40 adheres the cover layer 10 to the absorbent element 30 in a pattern coated absorbency zone 50 in a substantially rectangular pattern. The hot melt adhesive may alternatively be located between the absorbent element 30 and the barrier layer 20 (not shown). Other adhesive patterns and application locations are illustrated in Figures 3 to 12.

[0023] For example, Figure 3, shows a top plan view of an absorbent article **301** having cover layer **310**, opposite longitudinal sides **302**, **303** in an hour-glass configuration and opposite transverse ends **304**, **305**. Liquid absorbing hot melt adhesive **40** is zone coated in absorbency zone **350** in a substantially rectangular pattern.

[0024] In the embodiment of the invention illustrated in Figures 4 and 5, there is shown sanitary napkin **401** having cover layer **401**, barrier layer **410**, absorbent element **430**, transfer layer **470**, and aqueous liquid absorbing hot melt adhesive **440** which has been foamed by mixing the adhesive with an inert gas. The foamed adhesive is then metered and dispensed through a nozzle onto a substrate, in this case the cover layer of a sanitary napkin. This technology is commercially available from the Nordson Corporation using their FoamMelt® processors and is disclosed more fully in *Dilnik et al.*, U.S. Patent No. 5,807,367, which is incorporated herein in its entirety. As shown in Figure 4, the foamed hot melt adhesive **440** has been applied to the body facing cover layer adjacent the longitudinal sides of the sanitary napkin **401** to form side gaskets **450**, **451** and end gaskets **460**, **461**. The hot melt adhesive **440** may alternatively be applied between the cover layer **410** and the subjacent absorbent element **430** (not shown).

[0025] Referring to Figures 6 and 7, there is shown an absorbent article, which for purposes of illustration is a sanitary napkin **601** having opposite longitudinal sides **602**, **603** and opposite transverse ends **604**, **605**. Referring to Figure 7, the sanitary napkin **601** of Figure 6 is shown in cross section, having an upper, body facing, cover layer **610**, a lower garment facing, barrier layer **620** and absorbent element **630** between the cover layer **610** and barrier layer **620**. Liquid absorbing hot melt adhesive **640** adheres the barrier layer **620** to the absorbent element **630** in a multi-line coated absorbency zone **650** in a substantially rectangular pattern.

[0026] Figure 8 shows a top plan view of an absorbent article **801** having cover layer **810**, opposite longitudinal sides **802**, **803** in an hour-glass configuration and opposite transverse ends **804**, **805**. Liquid absorbing hot melt adhesive **840** is applied in a curved line pattern to form opposite side absorbency zones **841**, **842** and opposite transverse end absorbency zones **843**, **844**.

[0027] Figures 9 and 10 show top plan view of absorbent articles **901**, **920**, respectively, having an adhesive pattern in a substantially hour-glass shape. Figure 9 has cover layer **910**, opposite longitudinal sides **902**, **903** in an hour-glass configuration and opposite transverse ends **904**, **905**. Referring again to Figures 9 and 10, liquid absorbing hot melt adhesive **940**, **960** is applied to the article to form an hour-glass shaped absorbency zone **950**, **965** (respectively).

[0028] Referring to Figures 11 and 12, there is shown an absorbent article, which for purposes of illustration is a sanitary napkin **1101** having opposite longitudinal sides **1102**, **1103** and opposite transverse ends **1104**, **1105**. Referring to Figure 12, the sanitary napkin **1101** of Figure 11 is shown in cross section, having an upper, body facing, cover layer **1110**, a lower garment facing, barrier layer **1120** and absorbent element **1130** between the cover layer **1110** and barrier layer **1120**. Liquid absorbing hot melt adhesive **1140** is adhered to the cover layer **1110** and to the absorbent element **1130** in a parallel line coated absorbency zone **1150**.

Example 1

[0029] The aqueous liquid absorbing hot-melt adhesive of the present invention was evaluated for its melt viscosity, adhesive strength (peel strength as measured on a polypropylene nonwoven fabric) and ability to absorb an aqueous saline solution (absorbent capacity) relative to a conventional hot melt adhesive. The conventional hot-melt adhesive was commercially available from the Fuller Company under the tradename HL-1491™. This is a standard hot-melt adhesive that is often used in the construction of absorbent articles such as sanitary napkins, panty liners, diapers and the like. The formulation of the conventional adhesive is believed to be in the following approximate proportions:

- 15-20% of a styrene-isoprene-styrene block copolymer having a 30% styrene content;
- 60 - 70% aliphatic or aromatic modified aliphatic tackifying resin
- 15-20% mineral oil
- < 2% anti-oxidant
- < 2% additional adjuncts (wax and polyethylene)

[0030] Two examples of the hot-melt adhesive of the present invention had the following formulas:

Sample A

[0031]

- 5.7% block copolymer (Vector DPX-552™)
- 33.7% tackifying resin (Foral 85™)
- 10.0% aq. liquid absorbing polymer (Aquacaulk TQU-5™)
- 40.0% superabsorbent particles (Aquakeep J55-P™)

10.5% plasticizer (Peg 600™) and
0.5% antioxidant (Ethanox 330™).

Sample B

[0032]

15.0% block copolymer (Vector DPX-552™)
25.0% tackifying resin (Foral 85™)
0.0% aq. liquid absorbing polymer (Aquacaulk TQU-5™)
45.0% superabsorbent particles (Aquakeep J55-P™)
15.0% plasticizer (Peg 600™) and
0.5% antioxidant (Ethanox 330™).

[0033] The results of the evaluation are provided in the following Table 1.

Table 1

	Commercial Sample	Sample A	Sample B
Viscosity @ 177°C, 101,000 (Centipoise)	1100	10,000	
Absorbent Capacity (g/g)	none	9.4	10.3
Peel Strength (lbs./in. width)	1.1	0.3	1.18

[0034] The commercially available hot-melt adhesive exhibited substantially no absorbency while the hot-melt adhesive of the present invention absorbed about 10 grams of liquid per gram of adhesive. Moreover, the adhesive composition of the present invention experienced no diminution of its adhesive strength.

Claims

1. A hot-melt adhesive that is capable of absorbing aqueous liquids which comprises:

about 10% to about 50% of a block copolymer;
about 20% to about 80% of a tackifying resin; and
about 1% to about 60% of an aqueous liquid-absorbing polymer.

2. The hot-melt adhesive according to claim 1 wherein the block copolymer is a linear or radial co-polymer structure having the formula (A-B)_x wherein block A is a polyvinylarene block, block B is a poly(monoalkenyl) block, x denotes the number of polymeric arms, and wherein x is an integer greater than or equal to one.

3. The hot-melt adhesive according to claim 2 wherein the block A polyvinylarenes is selected from the group consisting of Polystyrene, Polyalpha-methylstyrene, Polyvinyltoluene, and combinations thereof and wherein the Block B poly(monoalkenyl) blocks are selected from the group consisting of conjugated diene elastomers, hydrogenated elastomers and combinations thereof.

4. The hot-melt adhesive according to claim 3 wherein the conjugated diene elastomers are selected from the group consisting of polybutadiene and polyisoprene and wherein the hydrogenated elastomers are selected from the group consisting of ethylene butylene, ethylene propylene, polyisobutylene and combinations thereof.

5. The hot-melt adhesive according to claim 1 wherein the hot melt adhesive further contains absorbent thermoplastic polymers, super absorbent particles, tackifiers and plasticizers.

6. The hot-melt adhesive according to claim 1 wherein the tackifying resins are selected from the group consisting of natural resins, modified resins, glycerol esters of natural resins, glycerol esters of modified resins, pentaerythritol esters of natural resins, pentaerythritol esters of modified resins; polyterpene resins, copolymers of natural terpenes, terpolymers of natural terpenes, phenolic modified terpene resins and hydrogenated derivatives thereof, aliphatic petroleum resins and hydrogenated derivatives thereof, aromatic petroleum resin and hydrogenated deriv-

atives thereof, aliphatic petroleum resins, hydrogenated derivatives of aliphatic petroleum resins, aromatic petroleum resins, hydrogenated derivatives of aromatic petroleum resins, and combinations thereof.

7. The hot-melt adhesive according to claim 1 wherein the aqueous liquid absorbing polymers is selected from the group consisting of thermoplastic hydrogels and thermoplastic polymeric compositions which are formed from a water-soluble soft segment and one or more hard segments.

8. The hot-melt adhesive according to claim 7 wherein the hard segments are selected from the group consisting of polyurethane, polyamides, polyesters, polyureas, polypropylene oxide and combinations thereof.

9. The hot-melt adhesive according to claim 7 wherein the soft segments are selected from the group consisting of polyethylene oxide, polyvinyl alcohol, polyvinyl pyrrolidone, polyacrylamide, polysaccharide, polymaleic anhydride, and random copolymers of polyethylene oxide and polypropylene-oxide.

10. An absorbent article comprising a liquid permeable topsheet, a liquid impermeable barrier sheet, an absorbent element between the topsheet and the barrier sheet, wherein either the topsheet or the barrier sheet is adhered to the absorbent element with a hot melt adhesive which further comprises:

about 10% to about 50% of a block copolymer;
about 20% to about 80% of a tackifying resin; and
about 1% to about 60% of an aqueous liquid-absorbing polymer.

11. An absorbent article comprising a liquid permeable topsheet, a liquid impermeable barrier sheet, an absorbent element between the topsheet and the barrier sheet, wherein at least a portion of the absorbent element contains a hot melt adhesive which further comprises:

about 10% to about 50% of a block copolymer;
about 20% to about 80% of a tackifying resin; and
about 1% to about 60% of an aqueous liquid-absorbing polymer.

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11





FIG. 12





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 12 5404

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 658 351 A (MCNEIL PPC INC) 21 June 1995 (1995-06-21)	1-6,10, 11	A61L15/58 A61L15/60
Y	* abstract * * page 3, line 1-7 * * page 4, line 14-54 * * page 5, line 21-37 * * page 8, line 13-27 *	1-11	
Y	EP 0 802 251 A (HERCULES INC) 22 October 1997 (1997-10-22) * abstract * * page 2, line 7-9 * * page 6, line 29-49 * * page 7, line 21-29 * * page 8, line 13 * * page 9, line 15-30 * * page 11, line 3-10 * * page 12, line 54,55 *	1-11	
A	US 5 503 919 A (LITCHHOLT JOHN J ET AL) 2 April 1996 (1996-04-02) * abstract * * column 1, line 9-13 * * column 3, line 7-24 * * column 16, line 17-35 * * column 24, line 47 - column 25, line 34 * * column 30, line 29-49; examples * * claims 1,2,5 *	1-4,6, 10,11	TECHNICAL FIELDS SEARCHED (Int.Cl.7) A61L A61F
A	US 5 750 623 A (DIEHL CHARLES F ET AL) 12 May 1998 (1998-05-12) * abstract * * column 7, line 9-20 * * column 8, line 5-23 *	1-6,10, 11	
-/-			
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 29 March 2000	Examiner Böhm, I
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03.82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 12 5404

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 5 372 870 A (DIEHL CHARLES F ET AL) 13 December 1994 (1994-12-13) * abstract * * column 1, line 18-31 * * column 2, line 55-65 * * column 3, line 14-33 * * column 6, line 1-17 *	1-6,10,11	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 29 March 2000	Examiner Böhm, I
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/02 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 12 5404

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

29-03-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0658351 A	21-06-1995	US 5462538 A	31-10-1995
		AT 171627 T	15-10-1998
		CA 2137513 A	17-06-1995
		DE 69413653 D	05-11-1998
		DE 69413653 T	11-03-1999
		ES 2123087 T	01-01-1999
		JP 7194651 A	01-08-1995
		US 5681305 A	28-10-1997
EP 0802251 A	22-10-1997	CA 2202192 A	15-10-1997
		CN 1172839 A	11-02-1998
		JP 10046128 A	17-02-1998
US 5503919 A	02-04-1996	US 5342858 A	30-08-1994
		AT 169952 T	15-09-1998
		AU 7313194 A	24-01-1995
		CA 2164812 A	12-01-1995
		DE 69412621 D	24-09-1998
		DE 69412621 T	25-02-1999
		EP 0706547 A	17-04-1996
		ES 2119217 T	01-10-1998
		JP 8512076 T	17-12-1996
		WO 9501408 A	12-01-1995
US 5750623 A	12-05-1998	CA 2252756 A	27-11-1997
		EP 0900258 A	10-03-1999
		WO 9744404 A	27-11-1997
US 5372870 A	13-12-1994	US 5292819 A	08-03-1994
		US 5143968 A	01-09-1992
		AU 2145092 A	30-12-1992
		DE 69223783 D	05-02-1998
		DE 69223783 T	10-06-1998
		EP 0588923 A	30-03-1994
		ES 2110502 T	16-02-1998
		JP 6509595 T	27-10-1994
		WO 9220725 A	26-11-1992
		US 5399627 A	21-03-1995
		AT 112795 T	15-10-1994
		AU 635559 B	25-03-1993
		AU 6186890 A	11-03-1991
		CA 2037926 A	12-02-1991
		DE 69013321 D	17-11-1994
		EP 0438576 A	31-07-1991
		ES 2061060 T	01-12-1994
		JP 4501285 T	05-03-1992

EPC FORM P/0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 12 5404

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

29-03-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5372870 A		KR 150188 B	01-10-1998
		NO 911394 A	04-06-1991
		WO 9102039 A	21-02-1991
		US 5358783 A	25-10-1994
		US 5292806 A	08-03-1994
		US 5266394 A	30-11-1993
<hr/>			

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82